

ROVING FOR SPRAY-UP

P218

Data sheet

This E-glass roving has a sizing system with a silane coupling agent. It has been designed to provide overall performance for spray-up applications.

Identification

P218 Spray-up roving

Technical characteristics (nominal values)

Linear weight of roving (tex)	Loss on ignition (%)	Moisture (%)
ISO 1889: 1997	ISO 1887: 1995	ISO 3344: 1997
2400	1.15	≤ 0.15

Packaging

Product	Pallet dimensions L x W (cm)	Levels per pallet	Cheeses per level	Total number of cheeses	Pallets	
					Approx. height (cm)	Net weight* (kg)
P218 spray -up roving	114 x 114	4	16	64	119	1300

* Add 35 to 45 kg to obtain gross weight.

Properties

- Easy rolling and de-airing



Roving for spray-up



Swimming pools



Sanitary

Storage

P218 roving should be stored dry and in its original packaging. The best conditions are temperature between 10 and 35°C and at a relative humidity between 35 and 85%.

If the product is stored at low temperature (below 15°C) it is necessary to put the pallets to be processed for at least 24 hours prior their use into processing area and remove a part of protective cover of the pallet to prevent condensation of humidity.

Static stacking of the pallets is possible one plus one (1/1), but it is recommended to use a plywood plate between the two pallets in order not to damage the lower pallet.

Edited by :



Business Unit
Reinforcements Europe
130, avenue des Follaz
F-73009 Chambéry
France
Tél: +33 (0)4 79 96 82 07
Fax: +33 (0)4 79 75 83 40

Saint-Gobain Vetrotex Reinforcement S.A.
130, avenue des Follaz – BP928
F-73009 Chambéry cedex
France
Tel: +33 (0)4 79 96 82 56
Fax: +33 (0)4 79 96 84 17

Saint-Gobain Vetrotex Reinforcement GmbH
Kaisertrasse 100
D-52134 Herzogenrath
Germany
Tel: +49 2407 9574 0
Fax: +49 2407 9574 22

Saint-Gobain Vetrotex Svenska AB
Kabelgatan 5
S-434 37 Kungsbacka
Tel: +46 0300 722 50
Fax: +46 0300 716 65

Vetrotex Distribucion Norte
Carretera Madrid-Barcelona Km 34,5
E-28800 Alcalá de Henares (Madrid)
Spain
Tel: +34 91 885 58 01
Fax: +34 91 885 58 15

Vetrotex Reinforcements Bohemia s.r.o.
Sokolovska 106
CZ 57021 Litomysl
Czech Republic
Tel: +420 464 651 111
Fax: +420 464 651 192

Saint-Gobain Vetrotex (UK) Ltd
Unit 2, Thames Park, Lester Way
Wallingford Oxon – OX10 9TA
Tel: +44 1 491 835 335
Fax: +44 1 491 822 712

Verigex srl
Via Giotto 3
I-20040 Cambiagio
Italy
Tel: + 39 02 959 481
Fax: + 39 02 953 491 92

Saint-Gobain Vetrotex reserves the right to change the information given herein without prior notice.

For further information our web site: www.vetrotexeurope.com

(04/2005)